



Acrovyn®

Stain Resistance and Cleanability

TYPICAL PHYSICAL PROPERTIES

ACROVYN STAIN RESISTANCE/CLEANABILITY

RESIDUAL STAIN AFTER CLEANING WITH:

STAINING AGENT

7 DAYS @ 75°F

SOAP & WATER*

MILD SOLVENT**

Mustard	None	None
Ketchup	None	None
Chocolate Syrup	None	None
Merthiolate	None	None
Lipstick	None	None
Vegetable Oil	None	None
Coffee	None	None
Tea	None	None
Wine	None	None
Coca Cola	None	None
Bleach	Slight	Slight
Crayon	Slight	None
Rit Dye - Marine Blue 44	Slight	None
10% Sulfuric Acid	None	None
10% Sodium Hydroxide	Slight	Slight
Pencil	Slight	None
Ink Pens	None	None

Cleaning Agents:

* Formula 409®, Lestoil, Fantastik®, or equivalent product

** Rubbing alcohol, naphtha type product, 50/50 mixture acetone/water



To download details, specs & photos visit www.c-sgroup.com
For technical and design assistance call 800-233-8493.

©Copyright 2008 Construction Specialties, Inc.

Construction Specialties, Inc. reserves the right to make design changes or withdraw any design without notice.