



Acrovyn®

Wall Covering Physical Properties

**TYPICAL PHYSICAL PROPERTIES
Acrovyn .040"/.060" WALL COVERING**

PROPERTY	TEST METHOD	TYPICAL VALUE
Specific Gravity	ASTM D-792	1.36
Tensile Strength	ASTM D-638	5,900 psi
Izod Impact (Strenght)	ASTM D-256	13 ft.-lbs./in.
Flexural Strength	ASTM D-790	9,500 psi
Flexural Modulus	ASTM D-790	330,000 psi
Thermal Coefficinet of LE	ASTM D-696	.00005 in./in./°F
Hardness Rockwell R	ASTM D-785	100
Heat Distortion Temp.	ASTM D-648	165°F