


Construction Specialties Inc. certifies that Model RS-9615 shown. Herein is licensed to bear the AMCA Seal. The ratings shown are based on tests and procedures performed in accordance with AMCA Publication 511 and comply with the requirements of the AMCA Certified Ratings Program. The AMCA Certified Ratings Seal applies to wind driven rain and air performance ratings only.

DESIGN DATA:

To maintain a **CLASS A (99%) effectiveness rating** with a 50 mph wind speed an rainfall rate of 8 in/hr

- Maximum intake core velocity 5.0 m/s (977 FPM)
- Maximum intake free area velocity 7.57 m/s (1490 FPM)
- Intake pressure drop 188 Pa (0.76 in. H₂O)
- Intake capacity 5.0 m³/s (10513 CFM)



*louver tested with 1m² core area, mill finish and no screen

SUGGESTED SPECIFICATIONS:

GENERAL: Furnish and install where indicated on the drawings C/S 5" (228.6 mm) STORM RESISTANT FIXED HORIZONTAL LOUVER **MODEL RS-9615** as manufactured by Construction Specialties, Inc., Cranford, NJ; Mississauga, Ontario. Complete details shall be submitted to the architect for approval prior to fabrication. The supplier must be a member of AMCA or BSRIA.


MATERIAL: Frames and blades to be fabricated from 6063-T6 aluminum alloy. Louver to be mechanically fastened using stainless steel or aluminum fasteners. Louvers to be supplied with 4" (101.6 mm) high by full depth sill flashing formed from minimum 0.050" (1.27 mm) thick aluminum. Sill flashing to have welded side panels. Louvers and sill flashing to be installed in accordance with the manufacturer's recommended procedures to ensure complete water integrity performance of louver system. All louvers to be furnished with 5/8" (15.87 mm) flattened expanded mesh, aluminum bird screen with a .055" (1.4 mm) thick extruded aluminum frame.

STRUCTURAL DESIGN: Structural supports shall be designed and furnished by the louver manufacturer to carry a wind load of not less than ____psf. (kPa). (Note: If this paragraph is omitted or if the design wind load is not specified, the louvers will be manufactured in self supporting units up to a maximum of 5' (1524 mm) wide by 8' (2438 mm) high. Any additional structural supports required to adequately secure these units within the opening shall be the responsibility of others.)

FINISH: All louvers shall be finished with C/S Powder Coat, a coating to be 1.5 to 3 mil. thick full strength **100% resin Fluoropolymer coating. Finish to allow zero VOCs** to be emitted into facility of application. Finish to adhere to a 4H Hardness rating. All finishing procedures shall be one continuous operation in the plant of the manufacturer. **The coating shall meet or exceed all requirements of AAMA specification 2605-5** "Voluntary Specification for High Performance Organic Coatings on Architectural extrusions and Panels." The louver manufacturer shall supply an industry standard **20-year limited warranty against failure or excessive fading** of the Fluoropolymer Powder Coat finish. This limited warranty shall begin on the date of material shipment.

WIND DRIVEN RAIN PERFORMANCE:

The louver test was based on a 39.370" (1.00 m) x 39.370" (1.00 m) core area unit tested at a rainfall rate of 8" per hour (203 mm/hr) and with a wind directed to the face of the louver at a velocity 50 mph (22.4 m/s). The test data shall show the water penetration effectiveness rating at each corresponding ventilation rate.



Discharge Coefficient
Intake Cd = 0.29 (Class 3)
AMCA certifies the coefficient class only


Core Ventilation Rate (m/s):	0.0	0.5	1.0	1.5	2.0	2.5	3.0	3.5	4.0	4.3	5.0
Core Ventilation Rate (ft/min):	0	98	197	295	394	492	591	689	787	854	977
Free Area Velocity (ft/min):	0	150	300	450	600	750	900	1050	1201	1302	1490
Rating Effectiveness:	A	A	A	A	A	A	A	A	A	A	A
Effectiveness Rating:	A = 1 to 0.99		B = 0.989 to 0.95		C = 0.949 to 0.80			D = 0.80 to 0			

PERFORMANCE DATA MODEL RS-9615

Width in Inches and Meters

	18	24	30	36	42	48	54	60
	0.46	0.61	0.76	0.91	1.07	1.22	1.37	1.52
18	0.93	1.33	1.72	2.12	2.52	2.92	3.31	3.71
0.46	0.09	0.12	0.16	0.20	0.23	0.27	0.31	0.34
24	1.34	1.92	2.50	3.07	3.65	4.22	4.80	5.38
0.61	0.12	0.18	0.23	0.29	0.34	0.39	0.45	0.50
30	1.76	2.51	3.27	4.02	4.78	5.53	6.29	7.04
0.76	0.16	0.23	0.30	0.37	0.44	0.51	0.58	0.65
36	2.18	3.11	4.04	4.97	5.91	6.84	7.77	8.71
0.91	0.20	0.29	0.38	0.46	0.55	0.64	0.72	0.81
42	2.59	3.70	4.81	5.93	7.04	8.15	9.26	10.37
1.07	0.24	0.34	0.45	0.55	0.65	0.76	0.86	0.96
48	3.01	4.30	5.59	6.88	8.17	9.46	10.75	12.04
1.22	0.28	0.40	0.52	0.64	0.76	0.88	1.00	1.12
54	3.42	4.89	6.36	7.83	9.30	10.76	12.23	13.70
1.37	0.32	0.45	0.59	0.73	0.86	1.00	1.14	1.27
60	3.84	5.49	7.13	8.78	10.43	12.07	13.72	15.36
1.52	0.36	0.51	0.66	0.82	0.97	1.12	1.27	1.43
66	4.26	6.08	7.91	9.73	11.56	13.38	15.21	17.03
1.68	0.40	0.57	0.73	0.90	1.07	1.24	1.41	1.58
72	4.67	6.68	8.68	10.68	12.69	14.69	16.69	18.69
1.83	0.43	0.62	0.81	0.99	1.18	1.36	1.55	1.74
78	5.09	7.27	9.45	11.63	13.82	16.00	18.18	20.36
1.98	0.47	0.68	0.88	1.08	1.28	1.49	1.69	1.89
84	5.51	7.87	10.23	12.59	14.94	17.30	19.66	22.02
2.13	0.51	0.73	0.95	1.17	1.39	1.61	1.83	2.05
90	5.71	8.16	10.61	13.06	15.51	17.96	20.41	22.86
2.29	0.53	0.76	0.99	1.21	1.44	1.67	1.90	2.12
96	6.13	8.76	11.38	14.01	16.64	19.27	21.89	24.52
2.44	0.57	0.81	1.06	1.30	1.55	1.79	2.03	2.28
102	6.55	9.35	12.16	14.96	17.77	20.57	23.38	26.19
2.59	0.61	0.87	1.13	1.39	1.65	1.91	2.17	2.43
108	6.96	9.95	12.93	15.91	18.90	21.88	24.87	27.85
2.74	0.65	0.92	1.20	1.48	1.76	2.03	2.31	2.59
114	7.38	10.54	13.70	16.87	20.03	23.19	26.35	29.52
2.90	0.69	0.98	1.27	1.57	1.86	2.15	2.45	2.74
120	7.79	11.14	14.48	17.82	21.16	24.50	27.84	31.18
3.05	0.72	1.03	1.34	1.66	1.97	2.28	2.59	2.90
126	8.21	11.73	15.25	18.77	22.29	25.81	29.33	32.85
3.20	0.76	1.09	1.42	1.74	2.07	2.40	2.72	3.05
132	8.63	12.32	16.02	19.72	23.42	27.12	30.81	34.51
3.35	0.80	1.15	1.49	1.83	2.18	2.52	2.86	3.21
138	9.04	12.92	16.80	20.67	24.55	28.42	32.30	36.17
3.51	0.84	1.20	1.56	1.92	2.28	2.64	3.00	3.36
144	9.46	13.51	17.57	21.62	25.68	29.73	33.79	37.84
3.66	0.88	1.26	1.63	2.01	2.39	2.76	3.14	3.52
150	9.88	14.11	18.34	22.57	26.81	31.04	35.27	39.50
3.81	0.92	1.31	1.70	2.10	2.49	2.88	3.28	3.67
156	10.29	14.70	19.11	23.53	27.94	32.35	36.76	41.17
3.96	0.96	1.37	1.78	2.19	2.60	3.01	3.41	3.82
162	10.71	15.30	19.89	24.48	29.07	33.66	38.24	42.83
4.11	0.99	1.42	1.85	2.27	2.70	3.13	3.55	3.98
168	11.12	15.89	20.66	25.43	30.20	34.96	39.73	44.50
4.27	1.03	1.48	1.92	2.36	2.81	3.25	3.69	4.13
174	11.53	16.19	21.05	25.90	30.76	35.62	40.47	45.33
4.42	1.05	1.50	1.96	2.41	2.86	3.31	3.76	4.21
180	11.75	16.78	21.82	26.85	31.89	36.93	41.96	47.00
4.57	1.09	1.56	2.03	2.49	2.96	3.43	3.90	4.37
186	12.16	17.38	22.59	27.81	33.02	38.23	43.45	48.66
4.72	1.13	1.61	2.10	2.58	3.07	3.55	4.04	4.52
192	12.58	17.97	23.37	28.76	34.15	39.54	44.93	50.33
4.88	1.17	1.67	2.17	2.67	3.17	3.67	4.17	4.68
198	13.00	18.57	24.14	29.71	35.28	40.85	46.42	51.99
5.03	1.21	1.72	2.24	2.76	3.28	3.80	4.31	4.83

Height in Inches and Meters



Construction Specialties, Inc.
Manufacturing & Sales Location
www.c-sgroup.com

Cranford, New Jersey
 49 Meeker Avenue 07016
 Telephone: (800) 631-7379
 Fax: (908) 272-2920

Mississauga, Ontario
 895 Lakefront Promenade L5E 2C2
 Telephone: (888) 895-8955
 Fax: (905) 274-6241

A member of the C/S Group of Companies
 For assistance with overseas requirements,
 call C/S International (908) 236-0800

©Copyright April 2010. Construction Specialties, Inc., reserves the right to make design changes or to withdraw any design without notice.

Upper Numerals English Units/Lower Numerals Metric Units