
Acrovyn 4000 Wall Covering Physical Properties

TYPICAL PHYSICAL PROPERTIES Acrovyn .040"/.060"/.075" WALL COVERING

PROPERTY	TEST METHOD	TYPICAL VALUE
Specific Gravity	ASTM D-792	1.31
Tensile Strength	ASTM D-638	5,715 psi
Flexural Strength	ASTM D-790	7,024 psi
Flexural Modulus	ASTM D-790	242,000 psi
Hardness (Shore D)	ASTM D-785	71
Heat Distortion Temp.	ASTM D-648	150.4°F